

Product Name : Oil Green 5602

General Properties

Appearance		Green Powder	Color Index Generic Name		C.I.Solvent Green 3
Moisture(Maximum %)		1.0	Chemical Constitution		Anthraquinone
pH		6.5 ± 1.5	Solubi -lity (%)	Methyl Alcohol	0.10 >
Melting Point(°C)		220 °C		Acetone	0.10
Resis tance to	Acid (5%HCl aq.)	5		Cyclohexanone	0.40
	Alkali (5%NaOH aq.)	5		Toluene	0.60
	Water (95°C 5min)	5		Ethyl Acetate	0.20

Fastness Properties

(Resins for use)

(Color Concentration)

P.S.	:	Stylon 666	Transparent	:	Color	0.05%
A.B.S.	:	Cycolac T	Opaque	:	Color	0.05%
P.M.M.A.	:	Delpet 80N		:	TiO2	0.5%
P.A.	:	UBE Nylon 1022B				
P.C.	:	Lexan 101-111				

Resin	Transparent						Opaque					
	Light Fastness		Heat Resistance (°C 5minutes)				Light Fastness		Heat Resistance (°C 5minutes)			
	50 hrs.	100 hrs.	240	260	280	300	50 hrs.	100 hrs.	240	260	280	300
P.S.	5	5	5	5	5	5	5	5	5	5	5	5
A.B.S.	4	3-2	5	5-4	3	2	5	4-3	5	5	5-4	3
P.M.M.A.	5	5	5	5	5	5	-	-	-	-	-	-
P.A.	5	4	-	5	5-4	4	5-4	3	-	5	4	4-3
	100 hrs.	200 hrs.	300°C 10min.		320°C 10min.				300°C 10min.		320°C 10min.	
P.C.	5	5	5	5-4			-	-	-	-		

Extent of discoloration had be judged by gray-scale and indicated 5 rank.